


Product Dimensions and Weights

DIN 936 / ISO 4035 Technical Specifications

Metric DIN 936 Low Profile Thin Hex Nut

Visit our online store for product availability



D	S	E	M	WEIGHT IN KG(s)
				PER 1000 PCS
M8	13	14.38	5	4.0
M10	17	18.90	6	8.6
M12	19	21.10	7	12.1
M14	22	24.49	8	18.2
M16	24	26.75	8	20.1
M18	27	29.56	9	29.6
M20	30	33.53	9	36.3
M24	36	39.98	10	58
M27	40	45.20	12	90
M30	46	51.28	12	111
M33	50	55.37	14	155
M36	55	61.31	14	190
M39	60	66.44	16	260
M42	65	72.61	16	307
M48	75	83.91	18	460

All measurements are in mm

Aspen Fasteners 4807 Rockside Road, Suite 400, Independence, OH 44131 USA www.aspenfasteners.com | aspensales@aspenfasteners.com | 1-800-479-0056



Metric DIN 936 Low Profile Hex Nuts are similar to a hex jam nut (DIN 439) but with slightly different heights. They are thin hex nuts about half as thick as a regular hex nut. They are often used as lock nuts, where they are threaded up against a standard nut locking it in place or in any circumstance where a standard nut is too thick for an application, a hex jam nut can be a very useful alternative. Aspen Fasteners offers the following sizes for immediate delivery from stock: M8 to M42 in both A2 and marine grade stainless steel as well as brass and steel zinc in right hand and left had threads. Aspen Fasteners offers over 500,000 unique fastener products from stock in inch and metric standard in a variety of materials and finishes. The following sizes of metric DIN 936 Low Profile Hex Nuts are available for immediate shipping from stock: Diameters ranging from M2 to M60 in steel and A2 and marine grade A4 stainless steel. View parts by clicking on the following link: metric DIN 936 Low Profile Hex Nuts.

DIN (**D**eutsches Institut für **N**ormung - German Institute for Standardization) standards are issued for a variety of components including industrial fasteners as metric DIN 936 Low Profile Hex Nuts. The DIN standards remain common in Germany. Europe and globally even though the transition to ISO standards is taking place. DIN standards continue to be used for parts which do not have ISO equivalents or for which there is no need for standardization. In this case the ISO equivalent for DIN 936 is ISO 4035.

1) Mechanical properties of stainless steel for metric DIN 936 Low Profile Hex Nuts

Stainless steels can be divided into three groups of steel - austenitic. ferritic and martensitic. Austenitic steel is by far the most common type (>90% of commercial fasteners). The steel groups and strength classes are designated by a four-digit sequence of letters and numbers (eg A2-70) as shown in the following table. DIN EN ISO 3506 governs screws and nuts made from stainless steel.

			Screws. Nuts and Bolts						
Steel group	Steel grade	Strength class	Tensile strength N/mm ²	Tensile strength PSI	Dia range	Nut Load N/mm ²			
		50	500	70.000	<=M39	500			
Austenitic	A2 and A4	70	700	100.000	<=M20	700			
		80	800	118.000	<=M20	800			

The tensile stress is calculated with reference to the tensile stress area (see DIN EN ISO 3506-1979). Nuts to be paired with same grade of stainless steel screws

Steel group	Property Strength class	Made From	Characteristics
	50	A1. A2	Soft; cold worked. turned and soft pressed fasteners
Austenitic	70	A2. A4	Cold worked. normal strength formed fasteners
	80	A2. A4	Extreme cold worked. high strength. special applications

Aspen Fasteners 4807 Rockside Road, Suite 400, Independence, OH 44131 USA www.aspenfasteners.com | aspensales@aspenfasteners.com | 1-800-479-0056



2) Chemical composition of stainless steel metric DIN 936 Low Profile Hex Nuts

Grade	USA Grade	Material designation	Material no.	C %	Si ≤ %	Mn ≤ %	Cr %	Mo %	Ni %
	X 5Cr Ni 1810	1.4301	≤ 0.07	1.0	2.0	17.5 to 19.5	1	8.0 to 10.5	
A 2	A 2 304	X 2 Cr Ni 1811	1.4306	≤ 0.03	1.0	2.0	18.0 to 20.0	ı	10 to 12.0
		X 8 Cr Ni 19/10	1.4303	≤ 0.07	1.0	2.0	17.0 to 19.0	ı	11.0 to 13.0
A 4	A 4 316	X 5 Cr Ni Mo 1712	1.4401	≤ 0.07	1.0	2.0	16.5 to 18.5	2.0 to 2.5	10.0 to 13.0
A 4	310	X 2 Cr Ni Mo 1712	1.4404	≤ 0.03	1.0	2.0	16.5 to 18.5	2.0 to 2.5	10 to 13

3) Chemical composition of steel metric DIN 936 Low Profile Hex Nuts

PROPERTY CLASS		CHEM	ICAL COMP	TEMPERING			
	MATERIAL AND TREATMENT	С		Р	S	TEMPERING TEMP °C MIN.	
		min.	max.	max.	max.		
4.6. 4.8. 5.8. 6.8	Low or medium carbon steel	- 0.55		0.05	0.06	-	
8.8	Medium carbon steel quenched. tempered	0.25	0.55	0.04	0.05	425	
9.8	Medium carbon steel quenched. tempered	0.25	0.55	0.04	0.05	425	
10.9	Medium carbon steel additives e.g. boron. Mn. Cr or Alloy steel - quenched. tempered	0.20	0.55	0.04	0.05	425	
12.9	Alloy steel - quenched. tempered	0.20	0.50	0.035	0.035	380	



4) Mechanical properties of steel for metric DIN 936 Low Profile Hex Nuts

MECHANICAL PROPERTY		PROPERTY CLASS									
					8.8						
		4.8 5.6	5.8	5.8 6.8	Up to M 16	Over M 16	9.8	10.9	12.9		
Tensile Strength	Tensile Strenath nom.		400	500 600		800		900	1000	1200	
(Rm. N/mm²)	m	in.	420	500	520	600	800	830	900	1040	1220
\	m	in.	130	155	160	190	250	255	290	320	385
Vickers Hardness	max		250			320	336	360	380	435	
Drivell Headness	m	in.	124	147	152	181	319	242	266	295	353
Brinell Hardness	max.		238		385	319	342	363	412		
	min.	HR	71	79	82	89			-		
Rockwell Hardness		HRC	-	-	-	-	20	23	28	32	39
Rockwell naturiess		HR	95			99		-			
	max.	HRC	-	-	-	-	32	34	37	39	44
Yield Stress ReL.	nom.		320	300	400	480	-				
N/mm²	m	in.	340	300	420	480		-			
Stress at permanent	no	m.			-		6	640 720		900	1080
set limit N/mm²	m	in.	-			640	660	720	940	1100	

Disclaimer

Dimensional data and technical information for metric DIN 936 Low Profile Hex Nuts was obtained from publicly available sources and not acquired through standards agencies. It has been completed and compiled for reference purposes only; where discrepancies are found they are subject to change without notice. Aspen Fasteners makes no warranties or representations regarding the accuracy and validity of the compiled information and data. Contact the relevant standards authorities for accurate and detailed information.